TECHNICAL DATA SHEET

Version: 17.1.2012 Letoxit® SV 51

Description

Epoxy foaming system SV-051 is composed of four components:

component A-epoxy resin, component B-hardener, component C-foaming agent, component D- additive. Epoxy foaming system is intended mainly for laminate manufacturing. It can be applied separately or combined with other foams used as sandwich core, such as expanded polystyrene, polyurethane foam, PVC foam or acrylic foam.

Application

Epoxy foaming system can be applied for production of:

- -sailboards, boats and sport equipment
- -aircraft parts
- -in automotive industry and parts for bus production

Foaming system can be applied either manually or by automatic device.

Technical data

A. Resin

Properties of uncured resin

Property	Norm (method)	Characteristic
Visual aspect		viscosity liquid
Density at 20°C	ISO 1675/CSN 656 199	1,16 <u>+</u> 0,01 g/cm ³
Viscosity at 25°C	method cone-board	10-14 Pa.s

B. Hardener

Properties of hardener

Property	Norm (method)	Characteristic
Visual aspect		yellowish viscosity liquid
Viscosity at 25°C	method cone-board	6-10 Pa.s
Density at 20°C	ISO 1675/CSN 656 199	1,05 <u>+</u> 0,01 g/cm ³

Processing

Mixing ratio of individual components:

A:B:C:D = 100:47:0,5-3:0,2 mixing ratio. Degree of foaming is affected by many factors, so there is recommended measuring of foaming agent for each kind of product and testing. In case when this system is combinated with polystyrene gelcoat, the first there is necessary to do adhesiveness test. Unsuitable combination can cause disjunction from gelcoat or possibly can cause bubbles and clefts. Epoxy foaming system pot life is (100g at 20°C) approximately from 10 to 15 minutes and depends on quantity and temperature.

Curing time: 30 minutes at 60°C

Packing

Components are packaged separately in 20kg tin boxes and 200kg drums.

Storage

Six months in a closed cointainer at the temperature from 20-25°C at dry place.



tel: +420 572 433 711 fax: +420 572 433 700 email: 5M@5M.cz www.5M.cz LETOXIT® is registered trademark

TECHNICAL DATA SHEET

Safety during processing

See Safety data sheet

Producer and Supplier

5M s.r.o. Na Záhonech 1177 686 04 Kunovice Czech Republic

Letoxit® is a registered trademark of 5M s.r.o. company



tel: +420 572 433 711 fax: +420 572 433 700 email: 5M@5M.cz